## 4 Flute Variable Helix

### with Radius



### **GENERAL INFORMATION**

Our 4 flute variable helix end mill has a geometry design that will enable manufacturers to increase production in less time than conventional end mills. Our design starts out from front to back with a higher helix than the competitors in the marketplace. This gives a higher shearing action along with the variable stability to decrease any chatter or instability. Many manufacturers are using this tool in a wide variety of applications although the principles of the tool geometry are still the same. This tool makes more parts in less time than with any other end mill on the market today. This end mill will perform in almost all materials but the optimum materials it should be utilized in are ferrous type materials.

#### **APPLICATION SPECIFICATIONS**

Variable Helix End Mill: This mill has quickly become one of the premier nomenclatures in the business. There are several styles or designs for this tool that are sufficient in many different materials. This design has the broadest range and will perform the best in a majority of materials. The helix changes along the flutes, which give the mill increased stability during the cutting action. Substantial increases in speeds can be achieved with this design which should produce more parts faster with equal to better wear ability. We have added a small corner radius for added strength to the corners and a smoother overall cutting action. This tool is only available in nACo coating for high temperature materials.

### **COATING INFORMATION**

**nACo** - Is an extremely high heat resistant coating with high nanohardness. Especially suited for high performance milling and drilling with rigid set ups, nACo's hardness comes from it's nano-composite structure. Coating consists of nano crystalline AITiN grains embedded in an amorphous silicon nitride matrix.

All general information and application specifications are to be used as guides and starting points only. Because of the multitude of variables used in the milling process, use this information as a guideline only. All speeds and feeds are also suggested starting pints. They may be increased or decreased depending on machine condition, depth of cut, finish requirements, coolant, etc.



# 4 FLUTE VARIABLE HELIX




Material	SFM	chip load per tooth			
Material		1/8"	1/4"	1/2"	1"
Aluminum Alloys	1200	.0010	.0020	.0040	.0080
Carbon Steel	300-600	.0010	.0015	.0030	.0060
Cast Iron	350-550	.0010	.0015	.0030	.0060
Copper Alloys	500-900	.0010	.0020	.0030	.0060
Steel - Annealed	350-500	.0010	.0020	.0030	.0050
Steel - Rc 18-24	150-500	.0004	.0008	.0015	.0045
Steel - Rc 25-37	125-200	.0003	.0005	.0010	.0030
Stainless Steel - Free Machining	250-400	.0005	.0010	.0020	.0030
Stainless Steel - Other	150-300	.0005	.0010	.0020	.0030
Inconel/ Monel	60-100	.0005	.0010	.0015	.0030
Titanium	175-300	.0005	.0008	.0015	.0030







Plunge/Slot



Profiling / Finishing



Profiling / Roughing

Note: All speeds and feeds are suggested starting points. They may be increased or decreased depending on machine condition, depth of cut, finish required, coolant, etc.

Carbide end mills are manufactured on CNC grinders to insure consistent flute spacing. Carbide end mills should be used in rigid tool holders to maximize tool life.

# PROBLEMS / SOLUTIONS

Problem/Cause	Solution		
Breakage			
Feed is too heavy	Reduce feed rate		
Cut is too heavy	Decrease width and depth-of-cut		
Overhang of tool is too much	Hold shank deeper, use shorter end mill		
Wear is too much	Regrind at earlier stage		
W	ear		
Speed is too fast	Decrease spindle speed, use another coolant		
Hard work material	Use Coatings (TiN, TiCN, TiAIN)		
Improper speed and feed (too slow)	Increase feed and speed		
Improper helix angle	Change tool to correct helix angle		
Primary relief angle is too large	Change to smaller relief angle		
Recutting chips	Change feed and speed, Change chip size or clear chips with more coolant or air pressure		
Short 7	Tool Life		
Cutting friction is too much	Regrind at earlier stage		
Hard work material	Use Coatings (TiN, TiCN,TiAIN)		
Improper helix and relief angle	Change to correct helix angle and primary relief		
Chi <sub>l</sub>	pping		
Feed rate too heavy	Reduce feed rate		
Feed too heavy on first cut	Reduce feed rate on first cut		
Lack of rigidity (machine & holder)	Use better machine or tool holder or change parameters		
Lack of rigidity (tool)	Use shorter tool, hold shank deeper, try climb milling		
Tool cutting corner too sharp	Decrease primary relief and cutting angle, reduce radial width-of-cut		
Chip F	Packing		
Cut too heavy	Decrease width and depth-of-cut		
Not enough chip clearance	Use end mill with less flutes		
Not enough coolant	Use higher coolant pressure and reposition nozzle to point of cut or use air pressure		

# PROBLEMS / SOLUTIONS

Burrs			
Wear on primary relief is too much	Regrind earlier stage		
Incorrect feed and speed rates	speed rates Correct cutting parameters		
Improper helix angle	Change to correct cutting angle		
Rough Surface Finish	Start operation with initial surface cut		
Feed rate too heavy	Reduce feed rate		
Cutting speed is too slow	Increase RPM		
Wear is too much	Regrind at earlier stage		
No end tooth concavity	Grind concave angle on bottom teeth		
Recutting chips	Change feed and speed, change chip size or clear chips with coolant or air pressure		
Chattering			
Feed and speed too fast	Correct feed and speed		
Lack of rigidity (machine & holder)	Use better machine or tool holder or change parameters		
Poor set up	Improve clamping rigidity		
Cut is too heavy	Decrease width and depth of cut		
Overhang of tool is too much	Hold shank deeper, use shorter end mill		
Lack of relief	Decrease relief angle, make margin: (touch primary with oil stone)		
Side Wall Tape	r in Work piece		
Feed rate too heavy	Reduce feed rate		
Overhang of tool is too much	Hold shank deeper, use shorter end mill		
Too few flutes	Use multi flute end mills, use end mill with higher rigidity		
No Dimensio	nal Accuracy		
Cut is too heavy	Decrease width and depth of cut		
Lack of accuracy (machine & holder)	Repair machine or holder		
Rigidity is not enough (machine & holder)	Change machine or tool holder or change parameters		
Too few flutes	Use multi flute end mills, use end mill with higher rigidity		



## RUSHMORE USA COATING INFORMATION

Coating	TiN Titanium Nitride	TiCN Titanium Carbontride	AITiN Aluminum Titanium Nitride	
Applications	General purpose coating for machining ferrous materials. Less expensive than AITiN coating. Good low cost alternative to AITiN in applications not generating extreme heat.	Steels over 40 Rc and aluminum alloys.	High performance coating for ferrous materials. Excellent high temperature resistance and hardness. Maintains high surface hardness at elevated temperature improving tool life and allowing faster feed rates. Produces aluminum oxide layer at high temperature which reduces thermal conductivity transferring heat into the chip.	
Materials	General purpose ferrous materials	Alloy steels, stainless steels, and in high speed cutting where moderate tempera- tures are generated at the cutting edges.	Alloy steels, stainless steels, tool steels, titanium, inconel, nickel and other aerospace materials.	
Color	Gold	Brown	Dark Grey - Black	
Structure	Mono-layer	Multi-layer	Multi-layer	
Hardness	24GPa	37GPa	Up to 38GPa	
Thermal Stability	1100° F	750° F	1450° F	

Coating	nACo Aluminum Titanium Nitride + Silicon Nitride	ZrN Zirconium Nitride	
Applications	Is an extremely high heat resistance coating with high nanohardness. Especially suited for high performance milling and drilling with rigid set ups. nACo's hardness comes from it's nano-composite structure. Coating consists of nano crystalline AITiN grains embedded in an amorphous silicon nitride matrix.	High hardness, lubricity and abrasion resistance. Improves performance over uncoated carbide in a wide variety of nonferrous materials. Less expensive alternative to diamond.	
Materials	Alloy steels, stainless steels, tool steels, titanium, inconel, nickel and other aerospace materials.	Abrasive non- ferrous alloys such as Brass, Bronze, Copper and Abrasive Aluminum Alloys	
Color	Black	Light Gold	
Structure	Multi-layer	Mono-layer	
Hardness	45GPa	24.6GPa	
Thermal Stability	1652° F	1100°F	

### RUSHMORE USA COATING INFORMATION

Material	Hardness	1st Choice	2nd Choice
Aluminum		ZrN	TiCN
Alloy Steel	16-23 HRc	AITiN	TiCN
Alloy Steel	23-38 HRc	AITiN	nACo
Alloy Steel	>38 HRc	nACo	AITiN
Carbon Steel	16-23 HRc	AITiN	TiCN
Carbon Steel	23-38 HRc	AITiN	nACo
Carbon Steel	>38 HRc	nACo	AlTiN
Hardened Steel	>42 HRc	nACo	AlTiN
Low Carbon Steel	13-23 HRc	AITiN	TiCN
Low Carbon Steel	23-38 HRc	AITiN	nACo
Low Carbon Steel	>38 HRc	nACo	AlTiN
Gray Cast Iron	18-22 HRc	nACo	AlTiN
Nodular Cast Iron	22-32 HRc	TiCN	nACo
Austenetic Stainless Steel	<35 HRc	TiCN	nACo
Martinsitic Stainless Steel	<35 HRc	nACo	AlTiN
Martinsitic Stainless Steel	>=35 HRc	nACo	AlTiN
Ni Alloys		nACo	AlTiN
PH Stainless Steel	<35 HRc	nACo	AlTiN
PH Stainless Steel	>=35 HRc	nACo	AlTiN
Ni, Co, Fe, Based Superalloys		nACo	AlTiN
High Si Aluminum		ZrN	TiCN
Titanium		nACo	AlTiN



# TECHNICAL GUIDE

### Confidential information for Rushmore sales purposes only.

Solid carbide end mills are rapidly replacing high speed steel end mills because production costs can be reduced as a result of the extreme metal removal rates which can be achieved with solid carbide end mills. When combined with the appropriate coating and the correct set up, optimal performance may be achieved.

It is important to comply with the following for the best performance results: Machine Capability: The machine must have the necessary rigidity to minimize spindle deflection and sufficient horsepower to perform at recommended speeds and feeds. Holders: Tool holders and collets must provide good concentricity between tool and machine spindle.

Workpiece: A secure and rigid workpiece to minimize deflection is needed. This is most important in climb milling operations. Because of the rigidity factor required in climb milling, speeds and feeds may be reduced by up to 25%.

